

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/EP05/001991

International filing date: 23 February 2005 (23.02.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/548,828
Filing date: 27 February 2004 (27.02.2004)

Date of receipt at the International Bureau: 29 March 2005 (29.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

17. 03. 2005

PA 1289144

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

March 03, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/548,828

FILING DATE: February 27, 2004

EPO - DG 1

17. 03. 2005

(76)

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



P. SWAIN

Certifying Officer

13142 U.S. PTO

PTO/SB/16 (01-04)

Approved for use through 07/31/2006. OMB 0651-0032

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. EL 975286709 US

14772 U.S. PTO
60/548828

022704

INVENTOR(S)					
Given Name (first and middle [if any])		Family Name or Surname		Residence (City and either State or Foreign Country)	
Glen P.		Rosini		Seabrook, Texas	
Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
POLYMERIZATION INITIATOR SYSTEMS CONTAINING ALUMINUM COMPOUNDS AS CURING INHIBITORS AND POLYM					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input type="checkbox"/> Customer Number: _____					
OR					
<input checked="" type="checkbox"/> Firm or Individual Name Akzo Nobel - Richard P. Fennelly					
Address Intellectual Property Department					
Address 7 Livingstone Avenue					
City Dobbs Ferry		State New York	Zip 10522-3408		
Country U.S.A.		Telephone	Fax (914) 693-4236		
ENCLOSED APPLICATION PARTS (check all that apply) (914) 674-5464					
<input checked="" type="checkbox"/> Specification Number of Pages 5					
<input type="checkbox"/> Drawing(s) Number of Sheets _____					
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76					
<input type="checkbox"/> CD(s), Number _____					
<input type="checkbox"/> Other (specify) _____					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.					
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees.					
<input checked="" type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: 01-1350					
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
FILING FEE Amount (\$) 160.00					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

[Page 1 of 2]

Respectfully submitted,

SIGNATURE

Richard P. Fennelly

TYPED or PRINTED NAME Richard P. Fennelly

TELEPHONE (914) 674-5464

Date Feb. 27, 2004

REGISTRATION NO. 25,677

(if appropriate)

Docket Number: ACA6328PRUS

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

POLYMERIZATION INITIATOR SYSTEMS CONTAINING ALUMINUM COMPOUNDS AS
CURING INHIBITORS AND POLYMERIZABLE COMPOSITIONS MADE THEREWITH

Background of the Invention

5 The present invention relates to a novel curing inhibitor
for amine organoborane complex polymerization initiators of the
type described and claimed in U.S. Patent Application Publication
No. 2002/0058764, the references described therein to Mottus et
al., Skoultchi, Zharov et al., and Pocius, in the following
10 related U.S. Patent Application Publication Nos. 2002/0025381,
2002/0028894, 2002/0031607, 2002/0033227, and 2003/0120005, and
in the original U.S. Patent Application No. 09/466,321. All of
these patent applications and patents are incorporated herein by
reference as covering the amine organoborane complex
15 polymerization initiators that are useful in the practice of the
present invention. As stated in at in paragraphs 0002 and 0009
of U.S. Patent Application Publication No. 2002/0058764, it is
desired to have polymerization initiator systems that have
enhanced stability in the presence of compounds having olefinic
20 unsaturation, thus improving the ability to cure on demand.

Summary of the Invention

One embodiment of the present invention is a composition
comprising an organoborane/amine complex and an effective amount
25 of an aluminum compound to inhibit curing of the
organoborane/amine complex when used as part of a polymerization
initiator system containing one or more monomers, oligomers or
polymers having olefinic unsaturation. Paragraph 0010 of U.S.
Patent Application Publication No. 2002/0058764 provides a non-
30 limiting but representative description of organoborane and amine
components that can be selected for use. The embodiments listed

in paragraphs 0011 and 0012 of this same patent publication are relevant to the use of this composition, and the statements made in paragraph 0013 regarding the characteristics of the composition also hold true for the composition of the present invention.

Description of Preferred Embodiments

Paragraph 0014 and the first seven lines of paragraph 0015 of U.S. Patent Application Publication No. 2002/0058764 describe the organoborane used in the complex while paragraphs 0017 to 0044 also describe certain amines that can be selected for use in the practice of the present invention. Other amines can also be used (for example, as described in U.S. Patent No. 5,935,711 in Cols. 5 to 8).

A variety of organoaluminum compounds of the formula Al_2R_6 can be selected for use in the present invention. In the preceding formula R is either C_1 - C_{12} alkyl or C_1 - C_{12} alkoxy, with each of the six R groups being the same or different. By extension, this formula also represents compounds explicitly designated as AlR_3 and $Al(R)(R')_2$ for compounds of the formula with even numbers of alkyl and/or alkoxy groups. The R groups can be a mixture of about three alkyl groups and about three alkoxy groups. The terms "alkyl" and "alkoxy" as used herein includes both straight-chain and branched-chain groups.

Non-limiting examples of organoaluminum compounds within the scope of this invention include trimethylaluminum, triethylaluminum, tri-n-propylaluminum, tri-n-butylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, aluminum triethoxide, aluminum isopropoxide, aluminum tri-s-butoxide, aluminum tri-t-butoxide, diethylaluminum ethoxide,

diisobutylaluminum ethoxide, triethyl(tri-s-butoxy)dialuminum, tri-n-butyl(triisopropoxy)dialuminum, and mixtures thereof.

The organoaluminum compound can either be added directly to the organoborane prior to reaction with amine to prepare the organoborane/amine complex or it can be added directly to the
5 preprepared organoborane/amine complex.

The molar ratio of boron to aluminum in the composition is relatively important. If the molar ratio of boron to aluminum is too high, then the polymerizable composition made therewith may
10 experience an undesirable increase in viscosity. If the molar ratio of boron to aluminum is too low, the composition may be pyrophoric (the absolute ratio at which the composition is pyrophoric is dependent upon the organoaluminum compound that is used) or there may be problems with adhesion. The molar ratio of
15 boron to aluminum can range from about 1.0:1.0 to about 50.0:1.0. Within this described range, for example, the molar ratio of boron to aluminum can range from about 10.0:1.0 to about 30.0:1.0.

U.S. Patent Application Publication No. 2002/0058764
20 describes the organoborane/amine complex (at paragraph 0045), the polymerizable compounds and compositions (at Paragraphs 0046 to 0048), the preparation and properties of the organoborane/amine complex (at paragraphs 0049 to 0051) and the applications of the polymerizable compositions (at paragraphs 0052 to 0071 and 0073
25 to 0075).

What is Claimed:

5 1. A composition comprising an organoborane/amine complex and an effective amount of at least one organoaluminum compound to inhibit curing of the organoborane/amine complex when used as part of a polymerization initiator system containing olefinic unsaturation.

10 2. A composition as claimed in Claim 1 wherein the organoaluminum compound is of the formula Al_2R_6 , with R being selected from the group consisting of C_1 - C_{12} alkyl and C_1 - C_{12} alkoxy and with each of the six R groups being the same or
15 different.

 3. A composition as claimed in either Claim 1 or Claim 2 having a molar ratio of boron to aluminum of from about 1.0:1.0 to about 50.0:1.0.

20 4. A composition as claimed in either Claim 1 or Claim 2 having a molar ratio of boron to aluminum of from about 10.0:1.0 to about 30.0:1.0.

25 5. A composition as claimed in any Claims 1 to 4 wherein the organoaluminum compound is one or more of trimethylaluminum, triethylaluminum, tri-n-propylaluminum, tri-n-butylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, aluminum triethoxide, aluminum isopropoxide, aluminum tri-s-
30 butoxide, aluminum tri-t-butoxide, diethylaluminum ethoxide,

diisobutylaluminum ethoxide, triethyl(tri-s-butoxy)dialuminum,
tri-n-butyl(triisopropoxy)dialuminum.

5 6. A composition as claimed in any Claims 1 to 5 wherein
the organoaluminum compound was added to an organoborane prior to
reaction with amine in preparing the organoborane/amine complex.

10 7. A composition as claimed in any Claims 1 to 5 wherein
the organoaluminum compound was added to a preprepared
organoborane/amine complex.

8. A polymerizable composition comprising one or more
monomers, oligomers or polymers having olefinic unsaturation and,
as the initiator system, the composition of any of Claims 1 to 7.